



TECHNICAL INFORMATION

ANTI-STAINS AQUA

DESCRIPTION:

Odourless water based paint for stains isolations, very short lapse time between application and utilization of the painted areas such as restaurants, offices, kitchens, bathrooms, hotels, public buildings, etc.

Features:

-) Solvents free.
-) Excellent adherence.
-) High coverage.
-) Isolate and cover stains of nicotine, smoke, grease, tannins, markers, etc.
-) Excellent leveling and brushability.
-) Eco friendly.
-) Odourless.

TECHNICAL DATA:

Fixed vehicle	Specials resins.	
Colour	White.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	60 %	UNE-EN ISO 3251
Solids by volume	33 %	UNE 48090
Viscosity	105 – 110 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.35 – 1.45 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	< 7.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	10 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	70 – 100 microns wet; 23 – 33 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/g): 30 g/l (2010). Max. content VOC: 3 g/l

APLICACION:

Isolating paint for stains of nicotine, grease, smoke, etc. Adequate for restaurants, offices, kitchens, bathrooms, hotels, public buildings, etc. Eco friendly and odourless.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ANTI-STAINS AQUA

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

-) Remove the dust and the paint in bad conditions and apply a first coat diluted 5% with water. After 6 hours apply the second coat no diluted. Apply a top coat of the product desired as finishing.
-) Consolidate and fix sandy supports with DECOKRILL PENETRANTE.
-) If there is fungus or algae formation clean previously.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres; 15 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>