



## TECHNICAL INFORMATION

### BRICK VARNISH

#### DESCRIPTION:

Acrylic varnish with a high resistance to wear and abrasion, avoiding the erosion of the support (cement, concrete, view face brick, stone, etc.). High adherence and hardness.

Features:

- ) Excellent adherence on supports.
- ) Resistant to erosion and weather.
- ) Excellent leveling and brushability.
- ) High hardness and scratch resistant.
- ) Resistant to chemical products.

#### TECHNICAL DATA:

Fixed vehicle	Acrylic thermoplastic resin.	
Colour	Colourless.	
Gloss	Gloss.	UNE-EN ISO 2813
Solids by weight	30 %	UNE-EN ISO 3251
Solids by volume	28 %	UNE 48090
Viscosity	45 – 55 KU (23 ± 2 °C)	UNE 48076
Specific weight	0.90 – 1.00 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	8 – 10 m <sup>2</sup> /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	100 – 120 microns wet; 28 – 34 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	24 hours.	
Traffic	48 hours.	
Traction adherence	> 6 N/mm <sup>2</sup> (cement board/7 days at 23 °C/100 $\hat{m}$ dry)	UNE-EN ISO 4824
Taber abrasion resistance	110 mg (CS-17 - 1Kg. - 1000 cycles)	UNE-EN ISO 7784-2
Persoz Hardness	84 seconds (200 $\hat{m}$ wet/7 days at 23 °C)	UNE-EN ISO 1522
Solvent	Aromatic solvent.	

EU limit value for this product (cat. A/h): 750 g/l (2010). Max. content VOC: 750 g/l

#### APLICACION:

Varnish transparent for protection and sealing surfaces of concrete, view face brick, stone, cement, etc., both indoors and outdoors, preventing them from absorbing water, dirt, grease, etc.

#### **Pinturas Decolor**

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5  
 Apdo. 106 – 02630 La Roda (Albacete) Spain  
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54  
 E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com) <http://www.decolor.com>



## TECHNICAL INFORMATION

### BRICK VARNISH

#### INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.  
Thinner and cleaning utensils: ACRYLIC SOLVENT.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

) Unpainted surfaces:

- Cement, concrete: Concrete must first be cured for which 1 month must have elapsed since application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10-15% to neutralize the alkalinity of cement, rinse and let dry. Apply the first coat diluted 15-20% with ACRYLIC SOLVENT as a primer. After 24 hours apply 2 coats diluted at most 5-10%.
- Other support: Painted surfaces must be dry and clean of dust, rust, grease, etc. Apply the first coat diluted 15-20% with ACRYLIC SOLVENT as a primer. After 24 hours apply 2 coats diluted at most 5-10%.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply BRICK VARNISH.

In general we recommend:

- ) Apply between 5 °C and 35 °C.
- ) It is not recommended to apply in full sun or high temperatures of the surface.
- ) Perfectly mix the product before use.

#### PRESENTATION:

Metallic packaging of: 1 Litre; 5 Litres; 20 Litres

#### STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.