



## TECHNICAL INFORMATION

### PASTA TEMPLE SMOOTH

#### DESCRIPTION:

Breathable temple paint, for interior decoration and protection of walls, formulated from a mixture of different types of carbonates of fine granulometry and great whiteness that are fixed with different tails, providing a smooth finish of great coverage and whiteness.

#### TECHNICAL DATA:

Colour	White and colours on request.	
Gloss	Matt	
Solids by weight	70 %	UNE-EN ISO 3251
Solids by volume	41 %	UNE 48090
Specific weight	1.60 – 1.70 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	Smooth 3 – 4 m <sup>2</sup> /Kg. and coat. Take in mind application leaking, surface irregularities, etc.	
Total drying	3 – 4 hours.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 1 g/l

#### APPLICATION:

Decoration and protection of interior walls in both new and old construction providing a smooth finish.

#### INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.  
Cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

Dilute the product between 20 – 25% of water depending on the desired viscosity for application.

If you want to tint you can use DECOLOR COLANT WATER BASE, maximum 5%.

In general we recommend:

- ) Apply between 5 °C and 35 °C.
- ) It is not recommended to apply in full sun or high temperatures of the surface.
- ) Perfectly mix the product before use it.

#### **Pinturas Decolor**

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5  
Apdo. 106 – 02630 La Roda (Albacete) Spain  
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54  
E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com) <http://www.decolor.com>



## TECHNICAL INFORMATION

### PASTA TEMPLE SMOOTH

---

#### PACKAGING:

Plastic bags of: 1 Kg., 2 Kg., 5 Kg., 13 Litres

#### STORAGE:

6 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

---

#### **Pinturas Decolor**

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>