



TECHNICAL INFORMATION

UNIVERSAL COLORANT

DESCRIPTION:

High concentrated pigment dispersion with a high tinting power.

Features:

-) High colorant power.
-) High compatibility with water base and solvent base products.
-) All UNIVERSAL COLORANT colorants are VOC and APEO free, meeting the latest environmental requirements.

TECHNICAL DATA:

Name	Colour	Specific weight (Kg/l)	Light fastness of pigment. Full (1-8)	Light fastness of pigment. Reduced (1-8)	Weather resistance of pigment. Full (1-5)	Weather resistance of pigment. Reduced (1-5)	Heat fastness of pigment. (°C)
YELLOW LEMON	Yellow P. YELLOW 3	1.15	7-8	7-8	4-5	4	200
YELLOW REAL	Yellow P. YELLOW 83	1.34	7-8	6-7	4-5	3	140
YELLOW OXIDE	Yellow Oxide P. YELLOW 42	1.56	8	8	5	5	180
RED	RED P. RED 112	1.10	8	6	4-5	3	180
RED OXIDE	Red Oxide P. RED 101	1.55	8	8	5	5	200
BLUE	Blue P. BLUE 15:3	1.10	8	8	5	4-5	200
GREEN	Green P. GREEN 7	1.18	8	8	5	4-5	200
BLACK	BLACK P. BLACK 7	1.16	8	8	5	5	200

APPLICATION:

Can be used with solvent or water based products.

INSTRUCTIONS FOR USE:

Cleaning utensils: Water.

Maximum recommended quantity per container: 10 %.

In general we recommend:

-) Perfectly mix the product before use.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

UNIVERSAL COLORANT

PRESENTATION:

Plastic packaging of: 0.125 Litres; 0.250 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>