



TECHNICAL INFORMATION

WALL-FIX AQUA

DESCRIPTION:

WALL-FIX AQUA is an under-coat paint or isolation paint for stains; it is odourless and fast drying. Time between coats is very short because of its fast drying time so it is recommend to be used in public areas such as offices, kitchens, hotels, public buildings, etc. Blocks and isolates the stains with the first coat and covers with the second ones.

Features:

-) Excellent adherence.
-) Excellent leveling and brushability.
-) Good chemical resistance.
-) Good covering power over satins of grease, nicotine, smoke, oil, etc.
-) Odourless.
-) No yellowing.
-) Washable after 15 days.
-) Eco friendly.
-) Solvent free.

TECHNICAL DATA:

Fixed vehicle	Special resins.	
Colour	White.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	61 %	UNE-EN ISO 3251
Solids by volume	46 %	UNE 48090
Viscosity	114 – 120 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.30 – 1.40 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	7.5 – 9.5 (a 23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	6 – 8 m ² /l. for full coverage. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	125 – 165 microns wet; 58 – 76 microns dry for full coverage.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 6 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

WALL-FIX AQUA

APPLICATION:

Isolate paint of smoke, grease, soot, stains of leaking water, marking pen, etc. Can be applied on brickworks in general, plaster boards, wood, etc. Suitable for walls and ceiling of restaurants, bars, kitchens, pubs, hotels, bathrooms, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

If the support is fixed apply before DECOKRILL PENTRANTE as a primer.

Apply a first coat dilute with water at 5%, next coats no diluted.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

If there is fungus or algae formations clean previously with an ADDITIVE FUNGICIDE - ALGICIDE. Is recommended on susceptible supports of forming fungus or algae, reinforce with ADDITIVE FUNGICIDE - ALGICIDE.

It is not recommended to apply on surfaces with permanent humidity.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres; 15 Litres

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

WALL-FIX AQUA

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>