



TECHNICAL INFORMATION

BASE DECORATIVA DECORATIVE COATINGS

DESCRIPTION:

Paint of high quality for decoration and protection of interior surfaces, only one coat. Base for decorative effects COSTA.

Features:

-) Excellent levelling.
-) Alkali resistant.
-) Good adhesion.
-) Reduced tendency to drip.
-) Fully washable after 15 days of application.
-) No splashes.
-) Only one coat.

TECHNICAL DATA:

Fixed vehicle	Resin vinyl-veova-acrylic.	
Solids by weight	62 %	UNE-EN ISO 3251
Solids by volume	42 %	UNE 48090
Viscosity	100 – 110 KU (23 + 2 °C)	UNE 48076
Specific weight	1.40 – 1.50 Kg./l (23 + 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 + 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 m ² /l with a covering power of 98%.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Wet scrub resistance	Class 2 (≥ 5 ↑m and < 20 ↑m for 200 wet scrub UNE-EN ISO 11998)	UNE-EN 13300

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 1,1 g/l

APLICACION:

Decorative coating for obtaining the effects.

INSTRUCTIONS FOR USE:

Application methods: brush or roller.

Dilution: Product ready for use.

Thinner and cleaning utensils: Water.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

BASE DECORATIVA DECORATIVE COATINGS

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

- Gypsum, cement and lime: Prime with DECOKRIL RAPID or DECOKRIL PIGMENTED. Apply BASE DECORATIVA.
- Iron, steel: Prime with PRIMER POLYVALENT AQUA. Apply BASE DECORATIVA.
- Wood: Prime with SEALER AQUA. Apply BASE DECORATIVA.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 3 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.