



TECHNICAL INFORMATION

DECORTEX ROUGH PREMIUM



DESCRIPTION:

Acrylic rough revetment for the protection and decoration of façades. Paint with a coating protect that provides an excellent protection against a wide range of fungus and algae.

Features:

-) Excellent exterior durability.
-) Good covering and filling power.
-) Protection and renovation of exterior mono-coat mortars.
-) Transpiring and waterproofing.
-) Alkaline and weather resistant.
-) Stable pigment and light resistant.

TECHNICAL DATA:

Fixed vehicle	Copolymer acrylic.	
Colour	Chart colours DECORTEX / IMPER-ELAST and tinting systems DECO-COLOR.	
Solids by weight	80 %	UNE-EN ISO 3251
Solids by volume	60 %	UNE 48090
Specific weight	1.60 – 1.70 kg/l (23 + 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 + 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	1 – 2 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	500 – 1000 microns wet; 300 – 600 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Permeability to water vapour	Class II (Medium)	UNE-EN ISO 7783-2
Liquid water transmission rate	Class II (Medium)	UNE-EN 1062-3
Classification	EN 1062-1 G ₃ E ₅ S ₃ V ₂ W ₂ A ₀ C ₀	UNE-EN 1062-1

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 10 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

DECORTEX ROUGH PREMIUM



APPLICATION:

Rough acrylic revetment of high quality for the protection and decoration of all types of surfaces of concrete, exterior brickworks, renovation of mono-coat mortars on facades, etc. Paint with protection against fungus and algae.

INSTRUCTIONS FOR USE:

Application methods: Roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Gypsum, cement and lime: Prime with DECOKRIL or PENETRATING DECOKRIL. Apply DECORTEX ROUGH PREMIUM as a finishing.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT or PRIMER POLYVALENT AQUA. Apply DECORTEX ROUGH PREMIUM as a finishing.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply DECORTEX ROUGH PREMIUM as a finishing.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply DECORTEX ROUGH PREMIUM as a finishing.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good conditions, wash, sand and apply two coats of DECORTEX ROUGH PREMIUM as a finishing. For a better consistency and durability of the coating we advise to prime first the surface using DECOKRIL PENETRANT.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.



TECHNICAL INFORMATION

DECORTEX ROUGH PREMIUM



- J In case of presence of saline efflorescence:
- Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 14 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>