

TECHNICAL INFORMATION







PRIMER PROTECTION OF THE WOOD



DESCRIPTION

Primer of protection of the wood of high quality for the protection in depth of wood, both for interior and exterior.

Features:

-  Prevents the absorption of water, humidity and regulates transpiration of the wood, eliminating deformation and cracks.
-  Highlight the natural appearing of the wood.
-  No peeling off.
-  Micro porous film.
-  Breathable to water vapour (inside the wood).
-  Fast drying.

TECHNICAL DATA

Nature	Synthetics resins.	
Colour	Chart colours BARNIZ – LASUR.	
Solids by weight	10 %	UNE-EN ISO 3251
Solids by volume	8 %	UNE 48090
Specific weight	0.75 – 0.85 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	10 – 12 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Drying touch	4 – 6 hours at 23 °C and 55% relative humidity. Depend on air temperature and ventilation.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic y aromatic solvent.	

EU limit value for this product (cat. A/f): 700 g/l (2010). Max. content VOC: 700 g/l

APPLICATION

Impregnation treatment of wood to protect outdoors. Penetrating into the wood and prevents the absorption of water, humidity and regulates transpiration of the wood, eliminating deformation and cracks.

INSTRUCTIONS FOR USE

Application methods: brush or spray.

Thinner and cleaning utensils: SOLVENT SYNTHETIC AND FATTY.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

PRIMER PROTECTION OF THE WOOD



Painted surfaces must be dry and clean of dust, rust, grease, etc.

The number of coats to apply of tinted PRIMER PROTECTION OF THE WOOD will affect the obtained final colour.

The wood highly resinous must be cleaned previously with SYNTETIC AND GREASE SOLVENT, UNIVERSAL SOLVENT or ODOURLESS SOLVENT, to avoid problems during the drying.




Unpainted surfaces:

- Standard wood: Apply 1-2-3 coats waiting and sanding between application around 12 – 24 hours.

Painted surfaces:

- Remove paint and varnish by polishing or sanding until complete elimination. After that proceed as non painted surfaces

In general we recommend:

-  Apply between 5 °C and 35 °C.
-  It is not recommended to apply in full sun or high temperatures of the surface.
-  Perfectly mix the product before use.

PRESENTATION

Metallic packaging of: 250 ml; 750 ml; 4 L

STORAGE

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>