



TECHNICAL INFORMATION

FLOOR PRIMER AQUA



DESCRIPTION

Primer waterborne for interior and exteriors, it makes easier the adherence for following paint coats on cement, concrete, glass, tiles, ceramic, etc.

Features:

- ✚ Excellent adherence on surface cement, concrete, glass, tiles, ceramic, etc.
- ✚ Equalizes the absorption of the support and maximizes the adherence.
- ✚ Resistant to water, and weather. No yellowish.
- ✚ Single component.
- ✚ Fast drying.
- ✚ Interior and exterior
- ✚ Eco friendly.

TECHNICAL DATA

| | | |
|----------------------------|---|---------------------|
| Nature | Acrylic resin. | |
| Colour | Colourless. | |
| Gloss | - | |
| Solids by weight | 31 % | UNE-EN ISO 3251 |
| Solids by volume | 29 % | UNE 48090 |
| Viscosity | 50 – 50 KU (23 ± 2 °C) | UNE 48076 |
| Specific weight | 0.95 – 1.05 kg/l (23 ± 2 °C) | UNE-EN ISO 2811-1 |
| pH | > 7.0 (23 ± 2 °C) | UNE-EN ISO 787-9 |
| Theoretical spreading rate | 10 – 14 m ² /l. Take in mind application leaking, surface irregularities, etc. | |
| Total drying | 1 hour. | UNE 48301 |
| Repaint | 6 hours. | |
| Solvent | Water. | |
| Reaction to fire | Class M-1 | UNE 23727 |
| Reaction to fire | Bs1d0 | UNE-EN 13501-1:2007 |

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 40 g/l

APLICACION

Waterborne primer it makes easier the adherence for following paint coats on cement, concrete, glass, tiles, ceramic, etc. for interior and exterior.

As primer and sealing supports concrete or cement, prior to application of coatings of floors.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

FLOOR PRIMER AQUA



INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.

Cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

PRODUCT READY FOR USE.

✚ Unpainted surfaces:

- Glass, tile, ceramic, etc.: Apply FLOOR PRIMER AQUA without dilution. Testing is recommended on non-porous surfaces.
- Cement and concrete: First concrete must be cured for which one month must have elapsed since its application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10-15% with water to neutralize the alkalinity of cement, then rinse and let dry. Apply FLOOR PRIMER AQUA without dilution.

✚ Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, sand and apply FLOOR PRIMER AQUA without dilution.

In general we recommend:

- ✚ Apply between 5 °C and 35 °C.
- ✚ The relative humidity < 80%.
- ✚ The surface humidity < 5%.
- ✚ The surface must be 3 °C over the dew point.
- ✚ Apply only on clean, dry surfaces and with a temperature above the dew point to prevent condensation or humidity.
- ✚ It is not recommended to apply in full sun or high temperatures of the surface.
- ✚ Perfectly mix the product before use.

PRESENTATION

Plastic packaging of: 4 L; 15 L

STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

FLOOR PRIMER AQUA



ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>