







**TECHNICAL INFORMATION****PAINT SPORTS RANGE****DESCRIPTION**

Paint water base for the protection and decoration of sports facilities.

Features:

-  Excellent adhesion to concrete substrates, cement, etc.
-  High mechanical resistance.
-  Exterior and interior.
-  Excellent leveling and brushability.
-  Alkaline and weather resistant.
-  Stables pigment and light resistant.

**TECHNICAL DATA**

Nature	Copolymer styrene acrylic.	
Colour	Oxide red, Green, Blue (RAL 5015).	
Gloss	Matt. 60°: 2-3 GU	UNE-EN ISO 2813
Solids by weight	60 %	UNE-EN ISO 3251
Solids by volume	43 %	UNE 48090
Viscosity	100 – 106 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.30 – 1.40 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	7 – 10 m <sup>2</sup> /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	100 – 140 microns wet; 45 – 60 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Traffic	48 – 72 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1	UNE-EN 13300
Slip resistance	Rd < 15 Class 0	UNE-EN 16165:2022

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 2 g/l

**APPLICATION**

Indicated to paint both indoors and outdoors of sports facilities.

**Pinturas Decolor**

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### PAINT SPORTS RANGE



#### INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.  
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.




##### Unpainted surfaces:

- Cement, concrete: Concrete must first be cured for which 1 month must have elapsed since application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10-15% to neutralize the alkalinity of cement, rinse and let dry. Apply the first coat as a primer FLOORS PRIMER AQUA or DECOKRIL RAPID. After 24 hours apply 2 coats diluted at most 5-10%.

##### Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply PAINT SPORTS RANGE.

In general, we recommend:

-  Apply between 5 °C and 35 °C.
-  It is not recommended to apply in full sun or high temperatures of the surface.
-  Perfectly mix the product before use.

#### PRESENTATION

Metallic packaging of: 4 L; 15 L

#### STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee.

For information about safety and the environment, please refer to the Safety Data Sheet. [www.decolor.com](http://www.decolor.com)

Quality control: this control is carried out in accordance with an ISO 9001-certified quality management system and an ISO 14001-certified environmental management system.

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5  
02630 La Roda (Albacete) Spain  
Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>