



TECHNICAL INFORMATION




CARIBE MATT PAINT



DESCRIPTION

Paint matt finishing for the decoration and protection of interior surfaces.

Features:

-  High covering power and great whiteness.
-  Excellent levelling and brushability.
-  Breathable.

TECHNICAL DATA

Nature	Copolymer styrene acrylic.	
Colour	White.	
Gloss	Matt G3. 85°: $5 < X < 10$	UNE-EN ISO 2813
Solids by weight	69 %	UNE-EN ISO 3251
Solids by volume	45 %	UNE 48090
Viscosity	117 – 123 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.65 – 1.75 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	6,5 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Opacity	Class 2	UNE-EN 13300
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 4	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 17,5 g/l

APPLICATION

For protection and decoration of plaster, cement and brickwork in general. Interior uses with little aggressive environments.

INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

CARIBE MATT PAINT



Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

✚ Unpainted surfaces:

- Gypsum, cement and lime: Apply PENETRATING DECOKRIL or apply the first coat diluted 10 – 15% with water. Apply two coats of MATT CARIBE as a finish.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT AQUA. . Apply two coats of MATT CARIBE as a finish.
- Wood: Prime with SEALER DECOLOR. Apply two coats of MATT CARIBE as a finish.
- "Dead" or powdery plaster: Prime with DECOKRIL or PENETRATING DECOKRIL. Apply two coats of MATT CARIBE as a finish.

✚ Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply MATT CARIBE.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

- ✚ Apply between 5 °C and 35 °C.
- ✚ It is not recommended to apply in full sun or high temperatures of the surface.
- ✚ Perfectly mix the product before use.
- ✚ In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
- ✚ In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION

Plastic packaging of: 3.5 L; 12 L

STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

CARIBE MATT PAINT



ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>