



## TECHNICAL INFORMATION

### D-600 MATT PAINT



#### DESCRIPTION

Acrylic 100% matt paint of high quality, for the protection and decoration of interior and exterior surfaces.

Features:

- ✚ High covering power, great whiteness and fully matt.
- ✚ No splattering.
- ✚ Fully waterproof and breathable.
- ✚ Weather and sunlight proof.
- ✚ Weatherproof and resistant to sunlight.
- ✚ Excellent brushability and levelling.
- ✚ Resistant to alkalis.
- ✚ Good adherence.
- ✚ Totally washable after 15 days.
- ✚ Paint with protection against fungi and algae.

#### TECHNICAL DATA

Nature	Copolymer acrylic.	
Colour	White.	
Gloss	Matt G4. 85°: ≤ 5	UNE-EN 13300
Solids by weight	65 %	UNE-EN ISO 3251
Solids by volume	43 %	UNE 48090
Viscosity	118 – 124 KU (23 + 2 °C)	UNE 48076
Specific weight	1.45 – 1.55 kg/l (23 + 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 + 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 m <sup>2</sup> /l. Take in mind application leaking, surface irregularities, etc.	
Opacity	Class 2	UNE-EN 13300
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 3 g/l

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### D-600 MATT PAINT



#### APPLICATION

Decorative and protective matt paint for both interior and exteriors, where is required and fine and beautiful finishing. For walls and ceilings of gypsum, plaster, plasterboard walls, walls with plaster or cement plaster, etc. Suitable for painted walls due to rain water impermeability and water vapour permeability.

#### INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.  
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

##### ✚ Unpainted surfaces:

- Gypsum, cement and lime: Apply a first coat diluted 10 – 15% with water or PENETRATING DECOKRIL. Apply two coats of MATT D-600 diluted to 10% with water for finish.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT AQUA. . Apply two coats of MATT D-600 diluted to 10% with water for finish.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply two coats of MATT D-600 diluted to 10% with water for finish.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply two coats of MATT D-600 diluted to 10% with water for finish.

##### ✚ Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply MATT D-600.
- If there is fungus or algae formations clean previously.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general, we recommend:

- ✚ Apply between 5 °C and 35 °C.
- ✚ It is not recommended to apply in full sun or high temperatures of the surface.
- ✚ Perfectly mix the product before use.
- ✚ In case of contamination by fungus or algae:
  - Wash with a solution of water and bleach to 10%.
  - Rinse with water.
  - Let dry completely before beginning to paint.
  - Use products with protection against FUNGUS.
- ✚ In case of presence of saline efflorescence:
  - Brush and wash with hydrochloric acid diluted to 10% with water.

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5  
02630 La Roda (Albacete) Spain  
Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### D-600 MATT PAINT



- Rinse with water.
- Let dry completely before beginning to paint.

#### PRESENTATION

Plastic packaging of: 750 ml; 4 L; 14 L

#### STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

---

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>