



TECHNICAL INFORMATION

MATT PAINT DECOMAT



DESCRIPTION

Matt paint for high quality based acrylic copolymers 100%, for the protection and decoration of Interior and exterior surfaces.

Features:

- Great power high whiteness and opacity.
- No splashes.
- Non-yellowing.
- Completely breathable and waterproof.
- Resistant to weather and direct sunlight.
- Excellent levelling and brushability.
- Good adhesion.
- Fully washable after 15 days of application.

TECHNICAL DATA

Nature	Copolymer acrylic.	
Colour	Base P – D – TR.	
Gloss	Matt G4. 85°: ≤ 5	UNE-EN 13300
Solids by weight	66 – 60 %	UNE-EN ISO 3251
Solids by volume	39 – 51 %	UNE 48090
Viscosity	110 – 120 KU (23 $\pm$ 2 °C)	UNE 48076
Specific weight	1.30 – 1.50 kg/l (23 $\pm$ 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 $\pm$ 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 – 12 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	80 – 125 microns wet; 30 – 50 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Permeability to water vapor	V ₁ (High)	UNE-EN ISO 7783-2
Liquid water transmission rate	W ₂ (Medium)	UNE-EN 1062-3
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 1 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MATT PAINT DECOMAT



APPLICATION

Decorative and paint protection both outdoors and indoors. For walls and ceilings plaster, plasterboard, walls with plaster walls or plaster cement, etc. Suitable for painting facades because of its impermeability to rainwater and the interior water vapour permeability. Paint specially formulated and elaborated for being used in tinting systems.

INSTRUCTIONS FOR USE

Application methods: brush, roller or spray gun.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

Unpainted surfaces:

- Gypsum, cement and lime: apply a first layer of diluted to 15% with water or fix with DECOKRIL or PENETRATING DECOKRIL. As a finish, apply two coats of MATE DECOMAT BASE diluted to 10% with water.
- Iron, steel: primed with PRIMER POLYVALENT AQUA. Apply two coats of MATE DECOMAT BASE diluted to 10% with water.
- Wood: Primed with SEALER AQUA. Apply two coats of MATE DECOMAT BASE diluted to 10% with water.
- "Dead" or powdery plaster: set with PENETRATING DECOKRIL. Apply two coats of MATE DECOMAT BASE diluted to 10% with water.

Painted surfaces:

- If the painting is in poor condition, remove it completely and proceed as on unpainted surfaces.
- If the paint is in good condition, wash and sand and apply MATE DECOMAT BASE.

In general we recommend:

-  Apply between 5 °C and 35 °C.
-  It is not recommended to apply in full sun or high temperatures from the bracket.
-  Perfectly mix the product before use.
-  In case of contamination by mould, fungi or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with MOULD protection.
-  In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MATT PAINT DECOMAT



PRESENTATION

Plastic packaging of: 750 ml; 4 L; 15 L

STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>