



TECHNICAL INFORMATION







SATIN PAINT CARIBE



DESCRIPTION

Satin paint to protect and decorate interior and exterior surfaces.

Features:

-  High whiteness, coverage and no yellowing.
-  Good exterior and alkaline support resistance.
-  Excellent levelling and brushability.
-  Good adherence, flexibility and elasticity.
-  Smooth touch.
-  Very low tendency to drip.

TECHNICAL DATA

Nature	Vinyl copolymer.	
Colour	White.	
Gloss	Satin G2a. 60°: <10	UNE-EN 13300
Solids by weight	47 %	UNE-EN ISO 3251
Solids by volume	32 %	UNE 48090
Viscosity	98 – 104 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.25 – 1.35 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	5,5 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Opacity	Class 2	UNE-EN 13300
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 2,5 g/l

APLICACION

For decoration and protection of interior and exterior surfaces where you want to obtain a glossy finish of high quality. Indicated for wall and plaster ceiling, surface of plaster and cement.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>

TECHNICAL INFORMATION**SATIN PAINT CARIBE****INSTRUCTIONS FOR USE**

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

 Unpainted surfaces:






- Gypsum, cement and lime: Apply a first coat diluted 10-15% with water or PENETRATING DECOKRIL. Apply two coats diluted to 5% with water for finish.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT AQUA. . Apply two coats diluted to 5% with water for finish.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply two coats diluted to 5% with water for finish.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply two coats diluted to 5% with water for finish.

 Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply two coats diluted to 5% with water for finish.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-  Apply between 5 °C and 35 °C.
-  It is not recommended to apply in full sun or high temperatures of the surface.
-  Perfectly mix the product before use.
-  In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-  In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION

Plastic packaging of: 3.5 L; 12 L

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SATIN PAINT CARIBE



STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>