



TECHNICAL INFORMATION





SWIMMING POOLS PAINTS WATER BASED



DESCRIPTION

High quality paint indicated to be used in the protection and decoration of surfaces that are under the water.

Features:

-  Excellent leveling and brushability.
-  Resistant to abrasion and scratches.
-  Resistant to chemical products used for the treatment of swimming pools.
-  Resistant to fungus and seaweeds.

TECHNICAL DATA

Nature	Styrene acrylic copolymer.	
Colour	Blue, White, Turquoise, Beige, Light Beige, Gray	
Gloss	Matt. 60°: 2-3 GU	UNE-EN ISO 2813
Solids by weight	62 %	UNE-EN ISO 3251
Solids by volume	42 %	UNE 48090
Viscosity	92 – 98 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.40 – 1.50 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 – 10 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	100 – 125 microns wet; 42 – 52 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	12 – 24 hours.	
Contact with water	10 days aprox.	
Solvent	Water.	

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 1 g/l

APPLICATION

For protection and decoration of surfaces immersed in water.

INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Do not fill the pool until 10-12 days after painting.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SWIMMING POOLS PAINTS WATER BASED



Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

✚ Unpainted surfaces:

- Cement and concrete: Concrete must first be cured for which 1 month must have passed since application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10 – 15% to neutralize the alkalinity of cement, rinse and let dry.

Apply DECOKRIL RAPID for fixing the surface. Apply 2 coats of SWIMMING POOLS PAINTS WATER BASED for finish.

If there is fungus or algae formations clean previously.

✚ Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply SWIMMING POOLS PAINTS WATER BASED.
- If there is fungus or algae formations clean previously.

In general, we recommend:

- ✚ Apply between 5 °C and 35 °C.
- ✚ It is not recommended to apply in full sun or high temperatures of the surface.
- ✚ Perfectly mix the product before use.
- ✚ In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
- ✚ In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION

Metallic packaging of: 4 L; 15 L

STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION
SWIMMING POOLS PAINTS WATER BASED



ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee.

For information about safety and the environment, please refer to the Safety Data Sheet. www.decolor.com

Quality control: this control is carried out in accordance with an ISO 9001-certified quality management system and an ISO 14001-certified environmental management system.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>