



TECHNICAL INFORMATION

SWIMMING POOLS PAINT SOLVENT



DESCRIPTION

High quality paint indicated to be used in the protection and decoration of surfaces that are under the water.

Features:

- Excellent leveling and brushability.
- Resistant to abrasion and scratches.
- Resistant to chemical products used for the treatment of swimming pools.
- Resistant to fungus and seaweeds.

TECHNICAL DATA

Nature	Acrylic thermoplastic resin.	
Colour	Blue (S 1050-B), White, Turquoise, Beige, Light Beige, Gray	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	70 %	UNE-EN ISO 3251
Solids by volume	49 %	UNE 48090
Viscosity	85 – 95 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.40 – 1.50 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	8 – 10 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	100 – 125 microns wet; 49 – 61 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	12 – 24 hours.	
Contact with water	10 days aprox.	
Solvent	Aromatic solvent.	

EU limit value for this product (cat. A/i): 500 g/l (2010). Max. content VOC: 420 g/l

APPLICATION

For protection and decoration of surfaces immersed in water.

INSTRUCTIONS FOR USE

Application methods: brush, roller or spray.
Thinner and cleaning utensils: ACRYLIC SOLVENT.

Do not fill the pool until 10-12 days after painting.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SWIMMING POOLS PAINT SOLVENT



Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

✚ Unpainted surfaces:

- Cement and concrete: Concrete must first be cured for which 1 month must have passed since application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10 – 15% to neutralize the alkalinity of cement, rinse and let dry.

Apply FLOOR PRIMER for fixing the surface. Apply 2 coats of SWIMMING POOLS PAINTS SOLVENT for finish.

If there is fungus or algae formations clean previously.

✚ Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply SWIMMING POOLS PAINTS SOLVENT.
- If there is fungus or algae formations clean previously.

In general we recommend:

- ✚ Apply between 5 °C and 35 °C.
- ✚ It is not recommended to apply in full sun or high temperatures of the surface.
- ✚ Perfectly mix the product before use.
- ✚ In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
- ✚ In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION

Metallic packaging of: 4 L

STORAGE

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SWIMMING POOLS PAINT SOLVENT



ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee.

For information about safety and the environment, please refer to the Safety Data Sheet. www.decolor.com

Quality control: this control is carried out in accordance with an ISO 9001-certified quality management system and an ISO 14001-certified environmental management system.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>