



## TECHNICAL INFORMATION




### POOL EDGE RENOVATOR



#### DESCRIPTION

Pool coping and edge renewing paint. Does not alter the surface texture. This treatment is easy to apply and can be recoated. Provides protection against mold and algae. Wait 10 days before contact with water.

Features:

-  Resistant to abrasion and scratches.
-  Resistant to chemical products used for the treatment of swimming pools.
-  Resistant to fungus and seaweeds.

#### TECHNICAL DATA

Nature	Acrylic.	
Colour	Blue, White, Turquoise, Beige, Light Beige, Gray	
Gloss	Satin. 60°: 20-25 GU	UNE-EN ISO 2813
Solids by weight	48 %	UNE-EN ISO 3251
Solids by volume	33 %	UNE 48090
Viscosity	90 – 100 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.15 – 1.25 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	6 – 8 m <sup>2</sup> /l. Take in mind application leaking, surface irregularities, etc.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	6 – 8 hours.	
Traffic	48 – 72 hours.	
Water resistance	At 10 days.	
Liquid water transmission rate	W <sub>3</sub> (Low)	UNE-EN 1062-3
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Solvent	Water.	

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 45 g/l

#### APLICACION

Pool coping and edge renewing paint. Does not alter the surface texture. This treatment is easy to apply and can be recoated.

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5  
02630 La Roda (Albacete) Spain  
Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### POOL EDGE RENOVATOR



#### INSTRUCTIONS FOR USE

Application methods: Brush or roller.  
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

##### Unpainted surfaces:

If mold or algae are present, clean the surface beforehand.

Thoroughly clean the surface and open the pores, preferably using traditional mechanical methods. If this is not possible, treat the surface with a 10-15% diluted hydrochloric acid solution (rinse thoroughly with water if using hydrochloric acid and allow to dry).

Apply the first coat of DECOKRIL RAPID as a primer and allow to dry for 24 hours before applying subsequent coats.






Allow the application to cure for at least one week before filling the pool or allowing the surface to get wet.

##### Painted surfaces:

Remove all old paint, preferably using mechanical means.

Proceed as with unpainted surfaces.

In general, we recommend:

-  Apply between 5 °C and 35 °C.
-  It is not recommended to apply in full sun or high temperatures of the surface.
-  Perfectly mix the product before use.
-  In case of contamination by fungus or algae:
  - Wash with a solution of water and bleach to 10%.
  - Rinse with water.
  - Let dry completely before beginning to paint.
-  In case of presence of saline efflorescence:
  - Brush and wash with hydrochloric acid diluted to 10% with water.
  - Rinse with water.
  - Let dry completely before beginning to paint.

#### PRESENTATION

Metallic packaging of: 750 ml; 4 L

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5  
02630 La Roda (Albacete) Spain  
Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### POOL EDGE RENOVATOR



#### STORAGE

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee.

For information about safety and the environment, please refer to the Safety Data Sheet. [www.decolor.com](http://www.decolor.com)

Quality control: this control is carried out in accordance with an ISO 9001-certified quality management system and an ISO 14001-certified environmental management system.

---

#### Pinturas Decolor

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>