



TECHNICAL INFORMATION

CLASSIC TEAK OIL



DESCRIPTION:

Mixture of natural oils and resins, to care for and beauty wood. Suitable for unvarnished wood, including exotic and tropical ones.

Features:

-) The treated wood regains its natural balance and its original qualities of gloss, texture and colour. Sanding is not necessary for repainting.
-) It restores the natural oils that wood loses over time.
-) The wood is protected from stains and dust.
-) Protects against fungi and bacteria.
-) Brings out the natural grain of the wood.
-) Does not cause wood peeling.
-) Does not form a film, does not peel or crack.
-) Fast drying.
-) Withstands strong climatic changes, indoors and outdoors.

TECHNICAL DATA:

Fixed vehicle	Natural oils and resins.	
Colour	Colourless.	
Solids by weight	35 %	UNE-EN ISO 3251
Specific weight	0.80 – 0.90 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	12 – 18 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Total drying	4 – 6 hours at 23 °C and 55% relative humidity. Depend on air temperature and ventilation.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic hydrocarbons.	

EU limit value for this product (cat. A/f): 700 g/l (2010). Max. content VOC: 550 g/l

APLICACION:

Maintenance and renovation of woods, especially teak, exotic and tropical woods without varnish. Especially suitable for outdoor furniture, floors and wooden structures. Can also be used indoors.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

CLASSIC TEAK OIL



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Cleaning utensils: SYNTHETIC AND FATTY SOLVENT.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

The wood highly resinous must be cleaned previously with SYNTHETIC AND FATTY SOLVENT, UNIVERSAL SOLVENT or ODOURLESS SOLVENT, to avoid problems during the drying.

) Unpainted surfaces:

- Wood in general: Apply 1-2 coats with an interval of 12-24 hours between coats.

) Painted surfaces:

- Remove paint and varnish by polishing or sanding until complete elimination. After that proceed as unpainted surfaces.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metallic packaging of: 0.750 Litres; 4 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>