



## TECHNICAL INFORMATION

### DECOPLAST

#### DESCRIPTION:

Putty ready for use special for filling holes or cracks and repair any types of irregularities.

Characteristics:

- ) Excellent open time.
- ) Easy application and excellent sanding.
- ) High hardness and adhesion.
- ) High filling power.
- ) Exterior – Interior use.

#### TECHNICAL DATA:

Colour	White.	
Specific weight	1.70 – 1.80 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	7.0 – 8.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	1.75 – 1.85 Kg./m <sup>2</sup> /1 mm. Take in mind application leaking, surface irregularities, etc.	
Reaction to fire	A2 - s1 - d0 Combustible.	UNE-EN 13501-1:2007
Total drying	Layer of 1 mm: 5 – 6 hours Layer of 2 mm: 9 – 10 hours	UNE 48301
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011
Solvent	Water.	

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 2.5 g/l

#### APPLICATION:

Putty ready for use special for filling holes or cracks and repair any types of irregularities.

#### INSTRUCTIONS FOR USE:

Application methods: trowel or spatula.

Cleaning utensils: Water.

Ready for use.

Maximum thickness per coat 3 mm.

Surfaces must be dry and clean of dirty, dust, grease, etc.

In case of metallic surfaces, prime first with PRIMER POLYVALENT or PRIMER POLYVALENT AQUA.

#### **Pinturas Decolor**

Industrial Estate El Salvador Avenue 3<sup>a</sup>, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: [dptotecnico@decolor.com](mailto:dptotecnico@decolor.com)

<http://www.decolor.com>



## TECHNICAL INFORMATION

### DECOPLAST

---

In case of wood surfaces, prime first with SEALER or SEALER AQUA.

In general we recommend:

- ) Apply between 5 °C and 35 °C.
- ) It is not recommended to apply in full sun or high temperatures of the surface.
- ) Perfectly mix the product before use.

#### PRESENTATION:

Plastic packaging of: 0.250 Litres; 0.750 Litres; 4 Litres; 15 Litres

#### STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

#### ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.