



TECHNICAL INFORMATION

DECOPLAST



DESCRIPTION:

Putty ready for use special for filling holes or cracks and repair any types of irregularities.

Characteristics:

-) Excellent open time.
-) Easy application and excellent sanding.
-) High hardness and adhesion.
-) High filling power.
-) Exterior – Interior use.

TECHNICAL DATA:

Colour	White.	
Specific weight	1.70 – 1.80 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	7.0 – 8.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	1.75 – 1.85 Kg./m ² /1 mm. Take in mind application leaking, surface irregularities, etc.	
Reaction to fire	A2 - s1 - d0 Combustible.	UNE-EN 13501-1:2007
Total drying	Layer of 1 mm: 5 – 6 hours Layer of 2 mm: 9 – 10 hours	UNE 48301
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011
Solvent	Water.	

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 2.5 g/l

APPLICATION:

Putty ready for use special for filling holes or cracks and repair any types of irregularities.

INSTRUCTIONS FOR USE:

Application methods: trowel or spatula.
Cleaning utensils: Water.

Ready for use.

Maximum thickness per coat 3 mm.

Surfaces must be dry and clean of dirty, dust, grease, etc.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

DECOPLAST



In case of metallic surfaces, prime first with PRIMER POLYVALENT or PRIMER POLYVALENT AQUA.

In case of wood surfaces, prime first with SEALER or SEALER AQUA.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.250 Litres; 0.750 Litres; 4 Litres; 20 Kg

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>