



TECHNICAL INFORMATION

DECOPLAST STANDAR POWDER

DESCRIPTION:

Powder putty special for filling holes and cracks and repair any type of irregularity in the surface.

Features:

-) Excellent open time.
-) Interior.
-) Easy to apply and sand.
-) High adherence and hardness.
-) Good filling power.

TECHNICAL DATA:

Colour	White.	
Theoretical spreading rate	1.75 – 1.85 Kg./m ² /1 mm. Take in mind application leaking, surface irregularities, etc.	
Total drying	Coat of 1 mm: 5 – 6 hours Coat of 2 mm: 9 – 10 hours	UNE 48301
Solvent	Water.	

APPLICATION:

Powder putty special for filling holes and cracks and repair any type of irregularity in the surface.

INSTRUCTIONS FOR USE:

Application methods: trowel or spatula.

Cleaning utensils: Water.

1/2 litre water 1 kilo of product, stir well and let stand for fifteen minutes dissolves. It can be done more or less fluid as work, increasing or decreasing the proportion of water.

Maximum thickness per coat 3 mm.

Surfaces must be dry and clean of dirty, dust, grease, etc.

In case of metallic surfaces, prime first with PRIMER POLYVALENT or PRIMER POLYVALENT AQUA.

In case of wood surfaces, prime first with SEALER or SEALER AQUA.

In general we recommend:

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

DECOPLAST STANDAR POWDER

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Packaging of: 1 Kg.; 5 Kg.; 15 Kg.

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>