



TECHNICAL INFORMATION

PAINT SPECIAL SATIN



DESCRIPTION:

Satin paint to protect and decorate interior and exterior surfaces.

Features:

-) High whiteness, coverage and no yellowing.
-) Good exterior and alkaline support resistance.
-) Excellent levelling and brushability.
-) Good adherence, flexibility and elasticity.
-) Smooth touch.
-) Very low tendency to drip.

TECHNICAL DATA:

Fixed vehicle	Copolymer vinyl.	
Colour	White.	
Gloss	Satin. 60°: 25-30 GU	UNE-EN ISO 2813
Solids by weight	54 %	UNE-EN ISO 3251
Solids by volume	39 %	UNE 48090
Viscosity	112 – 118 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.20 – 1.30 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	> 8.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	12 – 15 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	65 – 85 microns wet; 25 – 34 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1 (< 5 \hat{m} for 200 wet scrub UNE-EN ISO 11998)	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

EU limit value for this product (cat. A/b): 100 g/l (2010). Max. content VOC: 15 g/l

APLICACION:

Application and decoration of both indoor and outdoor surfaces, on supports made of concrete, plaster where you want to obtain a satin finishing.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

PAINT SPECIAL SATIN



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Gypsum, cement and lime: Apply a first coat diluted 10-15% with water or PENETRATING DECOKRIL. Apply two coats of SATIN SPECIAL diluted to 5% with water for finish.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT AQUA. Apply two coats of SATIN SPECIAL diluted to 5% with water for finish.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply two coats of SATIN SPECIAL diluted to 5% with water for finish.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply two coats of SATIN SPECIAL diluted to 5% with water for finish.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply SATIN SPECIAL.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 4 Litres; 9 Litres; 15 Litres

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

PAINT SPECIAL SATIN



STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>